

Epoxy Binder and Injection Resin

## DESCRIPTION



TamRez 220 is a high modulus, low viscosity, epoxy resin designed for injection into non-moving cracks in concrete structures. Its medium to low viscosity will allow maximum penetration into small cracks. TamRez 220 exhibits extremely high strength in its cured state, thereby restoring structural integrity. It is moisture insensitive, allowing for injection into damp cracks.

## KEY BENEFITS

- > Excellent adhesion
- > Moisture insensitive
- > Non-shrink
- > Pumpable
- > Aggregate extendable
- > Potable water certified

## TYPICAL APPLICATIONS

- > Pre-cast members
- > Injection of cracks in dry or damp concrete
- > Columns and beams
- > Bolt grouting
- > Joint reinstatement
- > Concrete repair mortars

## TECHNICAL DATA

TamRez 220	
Density EN ISO 2811	1.05 - 1.15
Viscosity EN ISO 3219	300 - 500 mPa·s
Mix ratio	2:1
Final cure	7 days
Minimum use temperature	15°C
Pot life and gel time (200g) ISO 9514	Pot life 60 min Gel time 90 min
Compressive strength BS6319:2	> 70 MPa
Flexural strength BS6319:3	> 80 MPa
Tensile strength BS6319:7	44 MPa
Maximum exotherm	< 60°C

All technical data stated herein is based on tests carried out under laboratory conditions at 25°C.

## APPLICATION GUIDELINES

As with any epoxy resin system, surface preparation is critical. Concrete surfaces or cracked sidewalls to which this product is to be applied should be cleaned by air or water. This will ensure a superior bond.

TamRez 220 may be used as a binder for epoxy mortars. We would recommend that a mix ratio of 4 parts (by weight) of fine clean sand is mixed with 1 part (by weight) of TamRez 220 to form a trowellable site mixed epoxy mortar.

TamRez 220 may also be used as a binder for epoxy pebbles to give the "golden look" or "wet look". We recommend that 10 parts (by weight) of clean dry pebbles are mixed with 1 part (by weight) of TamRez 220 and placed with a steel trowel.

Note: It is recommended that the material is conditioned to appropriate temperatures for at least 12 hours prior to application.

For further information on mixing and application techniques, please contact your local Normet representative.

Epoxy Binder and Injection Resin

## Subsequent Finishes / Ongoing Maintenance

We recommend the use of TamRez Cleaner. Clean equipment immediately after use.

## STORAGE

TamRez 220 should be stored at room temperature (min 10°C and max 38°C), kept dry and out of direct sunlight. If these conditions are maintained and the product packaging is unopened, then a shelf life of one year can be expected.

## HEALTH & SAFETY

TamRez 220 should only be used as directed. We always recommend that the Safety Data Sheet (SDS) is carefully read prior to application of the material. Our recommendations for protective equipment should be strictly adhered to for your personal protection. The Safety Data Sheet is available upon request from your local Normet representative.